



## Octocure 573

CHEMICAL NAME                      Zinc Oxide

PHYSICAL FORM:                      Aqueous, liquid dispersion

### PRODUCT SPECIFICATIONS

### METHODS

Solids, %	59.0 - 61.0	WI-SCC-040
Viscosity, cps.	100 - 500	WI-VDC-070
pH	10.0 – 11.5	WI-PHC-010
Particle Size, microns	0 – 2.0	WI-PSC-300

### PRODUCT DESCRIPTION:

Octocure 573 zinc oxide dispersion is readily incorporated directly into latex emulsion compounds. Zinc oxide is a commonly used ingredient for the pigmentation and vulcanizing of latex rubber. Normal use level is 1.0 - 4.0 parts per hundred in SBR and Natural latex. Octocure 573 is based on French process zinc oxide having a surface area of 8 to 10 m<sup>2</sup>/g.

Zinc oxide has approval by the FDA for use under the following: CFR 21, Sections 175.105, 175.300, 176.170, 176.180, 176.210, 177.1210, 177.1650, and 177.2600. It is the responsibility of the manufacturer of the FINAL article to ensure that the article complies with the extraction limitations and other limitations, including use limitations, applicable to its intended use and is technically suitable for that particular use.

### STORAGE AND HANDLING:

Containers should be kept tightly closed; avoid direct sources of heat or sunlight when possible. Once a drum has been opened, it is important not to introduce bacteria into the drum. Make sure the part drum is used quickly and that all stock is rotated on a first-in, first-out basis. Protect from freezing. Store at 40 – 90 deg F. Contents should be stirred using mechanical agitation prior to use. Shelf life expected one year from date of manufacture provided the material is stored at proper temperatures and containers remain tightly closed.

03/16µpH;07/14;06/12;07/11;10/09;11/30/98

The information provided herein is believed to be reliable; however, no guarantees are made or liability assumed. Tiarco Chemical makes no claims or warranties concerning the suitability of the product for a particular use or purpose.

1300 Tiarco Dr. SW; Dalton, GA 30720 USA; Tele: 706-270-5959; Fax: 706-277-9039