



## Octocure 750

CHEMICAL NAME: Sulfur  
PHYSICAL FORM: Aqueous, liquid dispersion

### PRODUCT SPECIFICATIONS

### METHODS

Solids, %	64.0 - 66.0	WI-SCC-040
Viscosity, cps.	1500 – 5000	WI-VDC-070
pH	9.5 - 11.0	WI-PHC-010
Particle Size, microns	0 - 7.0	WI-PSC-300

### PRODUCT DESCRIPTION:

Octocure 750 is a 61.8 % active dispersion of rubbermaker's sulfur, milled to a uniformly small particle size for optimum activity. Recommended use level is 2.0 - 3.0 parts per hundred of polymer based on dry weight for the vulcanization of SBR and Natural rubber latex.

Sulfur has approval by the FDA for use under the following: CFR 21, Sections 175.105, 177.1210, 177.2600. It is the responsibility of the manufacturer of the FINAL article to ensure that the article complies with the extraction limitations and other limitations, including use limitations, applicable to its intended use and is technically suitable for that particular use.

All of the ingredients used in this product are listed on the TSCA Inventory.

### STORAGE AND HANDLING:

Containers should be kept tightly closed; avoid direct sources of heat or sunlight when possible. Once a drum has been opened, it is important not to introduce bacteria into the drum. Make sure the part drum is used quickly and that all stock is rotated on a first-in, first-out basis. Protect from freezing. Store at 40 – 90 deg F. Contents should be stirred using mechanical agitation prior to use. Shelf life expected one year from date of manufacture provided the material is stored at proper temperatures and containers remain tightly closed.

11/15;05/15;06/12;07/11; 10/09; 06/06

The information provided herein is believed to be reliable; however, no guarantees are made or liability assumed. Tiarco Chemical makes no claims or warranties concerning the suitability of the product for a particular use or purpose.

1300 Tiarco Dr. SW; Dalton, GA 30720 USA; Tele: 706-270-5959; Fax: 706-277-9039